



## COBALT POWDERS – Co

### Grades Available

Grades <sup>1)</sup>	FSSS µm	Morphology	Oxygen %	Chemical
Co S08	0.8 ± 0.2	Spherical	0.8 max	Co ≥ 99.8% Ni ≤ 0.01%
Co C08	0.8 ± 0.2	Cylindrical	0.8 max	Fe ≤ 0.01% Mn ≤ 0.01%
Co S12	1.2 ± 0.2	Spherical	0.5 max	Cu ≤ 0.01% Pb ≤ 0.01%
Co C12	1.2 ± 0.2	Cylindrical	0.5 max	Zn ≤ 0.01% Si ≤ 0.01%
Co C16	1.6 ± 0.2	Cylindrical	0.5 max	Ca ≤ 0.01% Mg ≤ 0.01%
Co S18	1.8 ± 0.2	Spherical	0.5 max	Na ≤ 0.01% S ≤ 0.01%
Co C22	2.2 ± 0.2	Cylindrical	0.5 max	C ≤ 0.02%
Co S25	2.5 ± 0.5	Spherical	0.5 max	
Co S60	6.0 ± 2.0	Spherical	0.4 max	
Co S180	18.0 ± 2.0	Spherical	0.4 max	

1) Specific requirements can be met

### Packing

Vacuum package in a aluminum bag or sealed package in a polyethylene bag  
Steel drum outside package  
1kg, 5kg, 25kg, 50kg or 100kg net per bag  
Analysis certificate is available for each lot